

DINITROL 530

Glass / Paint Primer

DINITROL 530 is a solvent containing, physically and chemically drying black primer which promotes the adhesion between the glass (in combination with the activator DINITROL 520) and paint and the direct glazing adhesive.

» **Compatible with all 1-component polyurethane DINITROL adhesives**

» **Rust protection for smaller scratches on paint**

» **In combination with the DINITROL adhesive system additional UV protection and long-term safety**



Equipment

DINITROL APPLICATION FOAM 6-P
Art. No. 1731500

DINITROL WOOLEN WIPER 3000-P
Art. No. 17328000

INDUSTRIE NITRILE-GLOVES XL 10-P
Art. No. 1734100

DINITROL 530

Art. No.	Size	Package	Color
12023	30 ml	bottle	black
12030	100 ml	bottle	black
12026	250 ml	bottle	black
12133	1 L	bottle	black

a brand of



DINOL GmbH Pyrmonter Straße 76, D-32676 Lügde, Germany
Tel. +49 (0) 5281-98 2 98-0, Fax +49 (0) 5281-98 2 98-60, www.dinol.com

06.2020

DINITROL 530

Technical Details

Characteristics

DINITROL 530 is a solvent containing, physically and chemically drying black primer which promotes the adhesion between the glass (in combination with the activator DINITROL 520) and paint and the direct glazing adhesive and acts as a UV protection. DINITROL 530 combines the following functions:

- Pre-treatment on glass and paint
- inhibits rust in small nicks and scratches
- compatible with all DINOL adhesive systems

Features

- Primer as adhesion promoter, corrosion & UV protector, activator in combination with DINITROL 520

- Excellent adhesion promoter
- Supports long term safety by the use of the DINITROL adhesive system

Method of use

Before use of the primer DINITROL 530 shake the bottle thoroughly until paint mixing balls rattles freely. Mix for an additional one minute. The application of the primer DINITROL 530 can be done manually by felt and/or an adequate tool. Due to its reactivity with moisture, the opened bottle has to be used within a few days. (Recommendation: 1 week)

This product is suitable for experienced professional users only.

Further information:

The following documents are available on request:

- Material safety data sheet
- DINOL pre-treatment chart

Safety precautions

According to 1907/2006 EC, the primer DINITROL 530 is mandatory: Symbol: F, Xn Storage between 0 and 35°C, in closed packaging in a dry and ventilated area.

Technical Data

Chemical base	Reactive polyurethane adducts
Colour	black liquid
Drying time	approx 5 min*
Solid content	33 ± 2%
Viscosity Brookfield	17 – 25 mPas
Density, 23 °C	990 ± 20 kg/m ³
Application method	felt / brush
Application temperature	+ 5°C – 40°C
Flash point	< 21°C
Flash-off time	min. 10 minutes* max. 72 hours
Coverage	approx 150 g/m ²
Shelf life	12 months
Available in	30 ml bottle, 100 ml bottle, 250 ml bottle, 1 L bottle

1) 23°C / 50% rf

For all relevant safety advices please read the material safety data sheet or the packaging label.